

SUMITUBE[®] FC3 TERMINAL INSULATION

UL & CSA

SEMI-RIGID POLYOLEFIN CUT PIECES 2.3 : 1 Shrink Ratio

UL / CSA RECOGNIZED 125° C 600 V



RoHS Compliant

TYPICAL FEATURES

- 1) SUMITUBE FC3 terminal insulation is flame retarded, polyolefin heat-shrinkable tubing that is recognized by Underwriters' Laboratories (UL) Subject 224 and certified by Canadian Standard Association (CSA).
- 2) SUMITUBE FC3 terminal insulation will shrink to less than 50% of its expanded diameter.
- 3) Shrink temperature is 130° C.
- 4) Operating temperature range is -55° C to +125° C.
- 5) SUMITUBE FC3 terminal insulation is specially sized, expanded and cut to fit over and strain relieve the most common sizes of all combinations of terminals, lugs, spades and disconnect devices.
- 6) SUMITUBE FC3 terminal insulation is supplied in 1" long pre-cut pieces.

STANDARD SIZES

TRADE SIZE	INSIDE DIAMETER AS SUPPLIED (MIN)		INSIDE DIAMETER AFTER RECOVERY (MAX)		WALL THICKNESS AFTER RECOVERY (NOM)	
	INCH	(MM)	INCH	(MM)	INCH	(MM)
#1	0.220	5.6	0.095	2.4	0.031	0.80
#2	0.300	7.6	0.125	3.2	0.031	0.80
#3	0.350	8.9	0.150	3.8	0.031	0.80
#4	0.460	11.7	0.200	5.1	0.031	0.80

Standard colors: Black

Standard package: 1" Long Cut Pieces (Also available in coil form per factory quote)

How to Order: (Type of material) (Size) (Color)

Example: FC3 #2 Black

FC3 SPECIFICATION VALUES

PROPERTY (UNITS)	TEST METHOD	REQUIREMENT
Physical: Tensile strength (psi) Elongation (%) Specific gravity Heat resistance (158° C, 168 hrs.) Elongation (%) Secant modulus (psi) Deformation (125° C 1 hr.) (%) Longitudinal change (%)	ASTM D 638 ASTM D 638 ASTM D 792 UL 224 ASTM D882 UL 224 AMS-DTL-23053	2000 min.. 200 min. 1.35 min. 100 min. 2.5 X 10 ⁴ min. 50 max. ±5
Electrical: Dielectric strength withstand (2,500V, 60 sec.) Original After aging (158° C, 168 hrs.) Volume resistivity (ohm-cm)	UL 224 UL 224 ASTM D 876	No breakdown No breakdown 1.0 X 10 ¹⁴ min.
Chemical: Copper stability (158° C 168 hrs.) Elongation (%) Water absorption (%) Flammability	UL 224 ASTM D570 UL 224 (All tubing flame test)	100 min. 0.5 max. pass

Specification reference: UL 224 125° C, 600V
 File E48762 YDPU2, Cat. No. SUMITUBE FC3 or 967
 CSA C-22.2 No. 198.1, 125° C, 600V File LR33298

Marking: #SUMITOMO-K CSA SR HS X PO TUBING 125° C SUMITUBE FC3

AEROSPACE AND DEFENCE AUSTRALIA

No.14/18 Blanck Street
 Motorway Business Park
 Ormeau QLD Australia 4208
 Tel (07) 5549 0077
 Fax (07) 5549 0088
 www.aerodefence.com.au

