

VERY FLEXIBLE POLYVINYLIDENE FLUORIDE 2 : 1 Shrink Ratio

MILITARY SPECIFICATION & UL



RoHS Compliant



Lead-Free

TYPICAL FEATURES

- | | |
|---|--|
| <p>1) SUMITUBE K3 is an extremely flexible, transparent, inherently flame retarded heat-shrinkable PVDF tubing that meets or exceeds the requirements of AMS-DTL-23053/18, Class 3.</p> <p>2) SUMITUBE K3 is tough and abrasion resistant in mechanical environments. It also has excellent resistance to solvents.</p> <p>3) Shrink temperature is 90° C. It has the lowest shrink temperature and greatest flexibility of any PVDF type tubing available.</p> | <p>4) Operating temperature range is -55° C to +150° C.</p> <p>5) SUMITUBE K3 is recommended for applications requiring clarity, flexibility and low shrink temperature, combined with the excellent fluid resistant capabilities of fluoropolymers.</p> |
|---|--|

STANDARD SIZES

SIZE	INSIDE DIAMETER AS SUPPLIED (MIN)		INSIDE DIAMETER AFTER RECOVERY (MAX)		WALL THICKNESS AFTER RECOVERY (NOM)	
	INCH	(MM)	INCH	(MM)	INCH	(MM)
3/64	.046	1.2	.023	0.6	.010	0.25
1/16	.063	1.6	.031	0.8	.010	0.25
3/32	.093	2.4	.046	1.2	.010	0.25
1/8	.125	3.2	.062	1.6	.010	0.25
3/16	.187	4.8	.093	2.4	.010	0.25
1/4	.250	6.4	.125	3.2	.010	0.25
3/8	.375	9.5	.187	4.8	.012	0.30
1/2	.500	12.7	.250	6.4	.012	0.30
3/4	.750	19.1	.375	9.5	.017	0.43
1	1.000	25.4	.500	12.7	.019	0.48

Standard Colors:	Clear. Colors available subject to factory acceptance and quote.			
Standard Package:	Spooled (S)			
How to Order:	(Type of Material)	(Size)	(Color)	(Packaging)
Example:	K3	1/4	Clear	S

K3 SPECIFICATION VALUES

PROPERTY (UNITS)	TEST METHOD	REQUIREMENT
Physical: Tensile strength (psi) Elongation (%) Specific gravity Low temperature flex. (-55° C) Heat shock (275° C, 4 hrs.) Heat resistance (250° C, 168 hrs.) Elongation (%) Secant modulus (psi) Longitudinal change (%)	ASTM D 638 ASTM D 638 ASTM D 792 AMS-DTL-23053 AMS-DTL-23053 ASTM D638 ASTM D882 AMS-DTL-23053	1500 min. 200 min. 1.9 max. no cracking no cracking 100 min. 2.5 x 10 ⁴ max. ±10
Electrical: Dielectric strength (volts/mil) Volume resistivity (ohm-cm)	ASTM D 876 ASTM D 876	500 min. 1.0 X 10 ¹² min.
Chemical: Copper stability (180° C, 168 hrs.) Elongation (%) Water absorption (%) Fluid resistance (23° C, 24 hrs.) Tensile strength (psi) Flammability Shrink temperature, nominal	UL 224 ASTM D570 AMS-DTL-23053 UL-224 VW-1	70% of unaged value min. 0.5 max. 1000 min. Pass 90° C

Specification references: AMS-DTL-23053/18B, Class 3
 UL224 File E70631 YDQS2

AEROSPACE AND DEFENCE AUSTRALIA

No.14/18 Blanck Street
 Motorway Business Park
 Ormeau QLD Australia 4208
 Tel (07) 5549 0077
 Fax (07) 5549 0088
www.aerodefence.com.au



Rev. 2/21/05